



KAUNAS UNIVERSITY OF TECHNOLOGY
FACULTY OF MECHANICAL ENGINEERING AND DESIGN
RESEARCH CENTRE FOR PLASTIC AND LEATHER PRODUCTS

Studentu str., 56, LT-51424 Kaunas, Lithuania
Tel.: 0037-37 300207, MOBILE: 00370 610 05190, fax: 0037-37 353989
E-mail: midf.pogtc@ktu.lt, virginija.jankauskaite@ktu.lt

Data: 27-06-2014

TEST REPORT
Nr. POGTC-052-06/14

Page 1 of 2

1. CUSTOMER

**KING MINDAUGAS TREINING
CENTER**

Karaliaus Mindaugo avenue 11,
Kaunas, LT-44287 Lithuania

2. MANUFACTURER

T-Tape Company

Hogebergdreef 60,
4645 EX Putte,
The Netherlands

3. SAMPLE DESCRIPTION:

Purpose of testing	Plastics quality assessment
Normative document	—
Destination	Plastic sheets
Type	IMMO+NS IW200/NS 1300228
Color	White
Perforation	Non-perforated
Thickness	2.0 mm
Coating	Non-coated
Label	

Principal executive

A. Lisauskaitė

Centre Manager

V. Jankauskaitė


4. Number and date of ordering: 10-06-2014
5. Sample received: 15-06-2014
6. Sample tested 17-06-2014 – 27-06-2014

7. RESULTS OF TEST

Normative reference, section clause	Parameter	Specification requirement	Sample results:	
			range	average
ISO 2781	Density	–	–	1.15 g/cm ³
LST EN ISO 527-1	Elastic modulus	–	–	307 MPa
LST EN ISO 527-2	Tensile strength ¹	–	20.0 – 21.1 MPa	20.4 MPa
LST EN ISO 527-3	Strain at break ¹	–	420 – 548 %	490 %
LST EN ISO 178	Flexural modulus ¹	–	374 – 583 MPa	456 MPa
–	Maximum elongation when activated ²	–	1510 – 1780 %	1625 %

NOTE:¹ Specimens were cut at various directions (⊥, ||).² Specimens activation and testing conditions: a) temperature $T = 65 \pm 1^\circ\text{C}$, b) duration $\tau = 2.5$ min; c) testing according to the requirements of standard LST EN ISO 527.**8. OTHER INFORMATION**

- 8.1. Test results are valid only for this object.
- 8.2. To reprint or duplicate test report in part without permission of Centre Manager is not allowed.

Principal executive	A. Lisauskaitė 	Centre Manager	V. Jankauskaitė 
---------------------	--	----------------	---